

THERMO PLASTIC OLEFIN

8710

TPO

Description

8710 is a flexible-type simply blended TPO designed for the extrusion molding.

Applications

- Extrusion products (Sheet, hose)
- General industrial products

Physical Properties	Unit	Test Method	Typical Value
MFR (230 °C, 2.16kg)	g/10min	ASTM D1238	1.2
Density	Kg/m ³	ASTM D792	869
Mechanical Properties			
Durometer A Hardness	-	ASTM D2240	79
Tensile Strength at Break	MPa	ASTM D412	3.7
Tensile Elongation at Break	%	Die C 500mm/min	270

Processing Conditions (Extrusion):

Cylinder Temperature: 170-210 °C

Die Temperature: 200-220 °C

Storage and Handling:

Avoid direct sunlight, avoid contact with eyes, avoid prolonged, repeated contact with skin and use adequate ventilation.

Regulatory Compliance:

Please visit Petro Rabigh website or contact Quality Assurance and Claim Handling Section:

Marketing&ProductDevelopmentDept.QA&CH.Section@petrorabigh.com

Disclaimer: © Petro Rabigh. All information supplied by or on behalf of Petro Rabigh in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and believed reliable, but Petro Rabigh assumes no liability whatsoever in respect of application, processing or use made of the provided information or products, or any consequence thereof. The user is solely responsible and liable with respect to the application, processing or use of the provided information or product, whose quality and other properties shall be verified, or any consequence thereof. No liability whatsoever shall attach to Petro Rabigh for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the provided information or products by the user. To the extent the user is entitled to disclose and distribute this document, the user may forward, distribute, and/or photocopy this copyrighted document only if unaltered and complete, including all of its headers, footers, disclaimers, and other information.

Kingdom of Saudi Arabia
Petro Rabigh
Marketing & Product Development
Quality Assurance & Claim Handling Section
Tel: +966 12 425 7189
Fax: +966 12 425 8224
www.petrorabigh.com