POLYPROPYLENE



PR/MKP/QAC/F-077

Rev. No.: 2.0

Reference Document No.: PR_MKP_QAC_P-001

January 2020

AV161

Polypropylene Block Copolymer for injection molding application

Description

AV161 is a polypropylene block copolymer formulated with nucleating agent and intended for general-purpose injection molding. Injection molding parts made from this resin exhibit high impact and high stiffness.

Applications

- Commodities
- Batteries
- Containers
- Chair bases
- Seat bases

| Resin Properties | Unit | Test Method | Typical Value |
|----------------------------------|-------------------|--------------------|---------------|
| MFR (230°C/2.16Kg) | g/10min | ASTM D1238 | 5.5 |
| Density | g/cm ³ | ASTM D792 Method A | 0.9 |
| Mechanical Properties* | | | |
| Tensile Strength at Yield | MPa | ASTM D638 | 25 |
| Tensile Strength at Break | MPa | ASTM D638 | 13 |
| Flexural Modulus | MPa | ASTM D790 | 1170 |
| Izod Impact, Notched 23 °C | kJ/m ² | ASTM D256 | 10 |
| Izod Impact, Notched -20 °C | kJ/m ² | ASTM D256 | 4.0 |
| Rockwell Hardness-R | | ASTM D785 | 90 |
| Thermal Properties* | | | |
| Vicat Softening Temperature @10N | °C | ASTM D1525 | 154 |
| Heat Deflection 0.45MPa | °C | ASTM D648 | 106 |
| Other | | | |
| Shrinkage MD/TD | % | SUMIKA | 1.4/1.4 |
| Flammability | | UL94 | HB |

*Test specimen preparation Method: Pursuant to ASTM D4101

Processing conditions: Recommended melt temperature: 190 - 230 °C.

Storage and handling: AV161 should be stored in a dry cool place with adequate ventilation and protected from UV-light at temperature below 50 °C. It is advisable to process polypropylene resins within 6 months after delivery.

Food Contact Compliance and other Regulations: Please visit Petro Rabigh website.

Disclaimer: © Petro Rabigh. All information supplied by or on behalf of Petro Rabigh in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and believed reliable, but Petro Rabigh assumes no liability whatsoever in respect of application, processing or use made of the provided information or products, or any consequence thereof. The user is solely responsible and liable with respect to the application, processing or use of the provided information or product, whose quality and other properties shall be verified, or any consequence thereof. No liability whatsoever shall attach to Petro Rabigh for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the extent the user is entitled to disclose and distribute this document, the user may forward, distribute, and/or photocopy this copyrighted document only if unaltered and complete, including all of its headers, footers, disclaimers, and other information.

Kingdom of Saudi Arabia Petro Rabigh Marketing & Product Development Quality Assurance & Claim Handling Section Tel: +966 12 425 7189 Fax: +966 12 425 8224 www.petrorabigh.com