

POLYAMIDE 6

S2700

(ISO)

PA6

Description

S2700 is a Polyamide 6 grade of low viscosity.

Applications

- Engineering Plastics (Compounding)

Physical Properties	Unit	Test Method	Typical Value	
Relative Viscosity (1%(w/v) in 96 % (w/w) sulfuric acid)	-	ISO 307	2.70	
Water Content	wt%	ISO 15512	≤ 0.06	
Extractable Content	wt%	Internal method	≤ 0.60	
Amino End Groups	meq/kg	Internal method	35-45	
Chip Size	no./g	Internal method	70 - 110	
Density	g/cm ³	ISO 1183-1	1.12	
Water Absorption (23°C in water)	%	ISO 62	11.1	
Water Absorption (23°C, 50%RH)	%	ISO 62	2.9	
Melting Point	°C	ISO 11357-3	219	
Mechanical Properties			Dry	5% Water
Tensile Yield Strength	MPa	ISO 527-1, 2	79	42
Tensile Elongation at Yield	%	ISO 527-1, 2	4	25
Tensile Elongation at Break	%	ISO 527-1, 2	32	68
Tensile Modulus	MPa	ISO 527-1, 2	2650	1400
Flexural Strength	MPa	ISO 178	109	33
Flexural Modulus	MPa	ISO 178	2600	650
Charpy Impact Strength (notched, 23°C)	kJ/m ²	ISO 179-1	5	13
Hardness Rockwell	R Scale	ISO 2039-2	120	98
Thermal Properties			Dry	5% Water
Heat Deflection Temperature (1.80MPa)	°C	ISO 75-1, 2	60	-
UL Ratings				
UL Flammability	-	UL94/1.6mm	HB	

The above data are typical laboratory values and are intended to serve as guides only.

Disclaimer: © Petro Rabigh. All information supplied by or on behalf of Petro Rabigh in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and believed reliable, but Petro Rabigh assumes no liability whatsoever in respect of application, processing or use made of the provided information or products, or any consequence thereof. The user is solely responsible and liable with respect to the application, processing or use of the provided information or product, whose quality and other properties shall be verified, or any consequence thereof. No liability whatsoever shall attach to Petro Rabigh for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the provided information or products by the user. To the extent the user is entitled to disclose and distribute this document, the user may forward, distribute, and/or photocopy this copyrighted document only if unaltered and complete, including all of its headers, footers, disclaimers, and other information.

Kingdom of Saudi Arabia
Petro Rabigh
Marketing & Product Development
Quality Assurance & Claim Handling Section
Tel: +966 12 425 7189
Fax: +966 12 425 8224
www.petrorabigh.com

POLYAMIDE 6

S2700

(ISO)

PA6

Storage and Handling:

Protect against physical damage. Containers of this material may be hazardous when empty since they retain product residues (dust, solids). Store in a cool, dry place. Protect it from moisture absorption and contamination.

Regulatory Compliance:

Please visit Petro Rabigh website or contact Quality Assurance and Claim Handling Section:
Marketing&ProductDevelopmentDept.QA&CH.Section@petrorabigh.com

Disclaimer: © Petro Rabigh. All information supplied by or on behalf of Petro Rabigh in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and believed reliable, but Petro Rabigh assumes no liability whatsoever in respect of application, processing or use made of the provided information or products, or any consequence thereof. The user is solely responsible and liable with respect to the application, processing or use of the provided information or product, whose quality and other properties shall be verified, or any consequence thereof. No liability whatsoever shall attach to Petro Rabigh for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the provided information or products by the user. To the extent the user is entitled to disclose and distribute this document, the user may forward, distribute, and/or photocopy this copyrighted document only if unaltered and complete, including all of its headers, footers, disclaimers, and other information.

Kingdom of Saudi Arabia
Petro Rabigh
Marketing & Product Development
Quality Assurance & Claim Handling Section
Tel: +966 12 425 7189
Fax: +966 12 425 8224
www.petrorabigh.com