

POLY METHYL METHACRYLATE EX PMMA

Description

EX is a Poly methyl Methacrylate general-purpose extrusion grade. It possesses excellent extrusion molding properties.

Applications

- Extrusion sheets for the manufacturing of signage and displays
- Sound barriers
- construction applications and light guide panels for general LED lighting
- Profile Extrusion products such as pipes and rods

Optical Properties	Typical Value	Unit	Test Method
Refractive Index	1.49	---	ISO 489
Total Light Transmittance	92	%	ISO 13468-1
Haze	<0.5	%	ISO 14782
Thermal Properties			
Coefficient of Linear Expansion	7×10 ⁻⁵	1/ °C	ISO 11359-2
Vicat Softening Temperature (VST)	104	°C	ISO 306
Deflection Temperature Under Load 1.82 MPa (annealed)	94	°C	ISO 75-2 Af
Melt Flow Rate (MFR) 230 °C, 37.3N (3.8kgf)	1.5	g/10min	ISO 1133
Mechanical Properties			
Tensile Strength at break	74	MPa	ISO 527-2
Tensile Strain at break	5	%	ISO 527-2
Flexural Strength	120	MPa	ISO 178
Flexural Modulus	3100	MPa	ISO178
Charpy Impact Strength (notched)	1.4	kJ/m ²	ISO 179-1
Rockwell Hardness Scale M	100	-	ISO 2039-2
Electrical Properties			
Surface Resistivity	> 10 ¹⁶	Ω	IEC 60093
Volume Resistivity	> 10 ¹⁵	Ω	IEC 60093
Insulation Resistance	> 10 ¹⁵	Ω	IEC 60167
Dielectric Strength	20	kV/mm	IEC 60243-1
Dielectric Constant (1MHz)	3.1	---	IEC 60250
Other Properties			
Specific Gravity	1.19	---	ISO 1183
Mold Shrinkage	0.2 -0.6	%	ISO 294-4
Water Absorption	0.3	%	ISO 62
Flammability	HB	---	UL 94

The above data are typical laboratory values and are intended to serve as guides only.

Disclaimer: © Petro Rabigh. All information supplied by or on behalf of Petro Rabigh in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and believed reliable, but Petro Rabigh assumes no liability whatsoever in respect of application, processing or use made of the provided information or products, or any consequence thereof. The user is solely responsible and liable with respect to the application, processing or use of the provided information or product, whose quality and other properties shall be verified, or any consequence thereof. No liability whatsoever shall attach to Petro Rabigh for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the provided information or products by the user. To the extent the user is entitled to disclose and distribute this document, the user may forward, distribute, and/or photocopy this copyrighted document only if unaltered and complete, including all of its headers, footers, disclaimers, and other information.

Kingdom of Saudi Arabia
Petro Rabigh
Marketing & Product Development
Quality Assurance & Claim Handling Section
Tel: +966 12 425 7189
Fax: +966 12 425 8224
www.petrorabigh.com

POLY METHYL METHACRYLATE EX PMMA

Processing Conditions:

Typical processing conditions are as follows:

Recommended Extrusion Molding Conditions		
EX		
Screw L/D		30 - 35
Cylinder Temp. °C	Hopper Side	200 - 210
	Center Side	230 - 240
	Die Side	240 - 245
Die Temp. °C		235 - 245
Recommended Annealing Conditions		
Temp. °C		75 - 85
Time/h		4

Storage and Handling:

PMMA is a thermoplastic and is flammable and soluble in organic solvents. Before using PMMA, please refer to the Safety Data Sheet (SDS) separately prepared by us.

PMMA should be stored in accordance with state and local regulations. In case of spillage, remove pellets immediately to prevent potential slipping hazard. PMMA should be kept away from direct sunlight, water and moisture and be stored at ambient temperature.

Regulatory Compliance:

Please visit Petro Rabigh website or contact Quality Assurance and Claim Handling Section:

Marketing&ProductDevelopmentDept.QA&CH.Section@petrorabigh.com